

22 Efal St. POB 3041 Kiryat-Arie, Petah-Tikva 49511, Israel • Tel: 972-3-9231311 • Fax: 972-3-9231511

Antistatic Futter fabric – FF48

■ Static dissipative knitted fabric

■ For use in manufacturing ESD garments such as Sweatshirt, Cardigans, Jumping-suits

- IEC 61340-5-1 compatible
- All colors available providing Pantone number or color sample
- Composition:
 48% polyester
 48% cotton
 4% conductive yarn
- Weight 280 g/sm
- Comfortable and breathable

Durability

IEC 61340-5-1 Electrical properties maintained after more than 40 industrial launderings

Machine washable up to 40[°] _c Do not bleach Do not use acid or alkali Ironing at Medium temperature Tumble dry at low temperature



22 Efal St. POB 3041 Kiryat-Arie, Petah-Tikva 49511, Israel • Tel: 972-3-9231311 • Fax: 972-3-9231511

Electrical properties:

	Test standard	Typical values	Requirements
Point to point resistance Rp	IEC 61340-5-1	10 ⁵ - 10 ⁷ Ω	Rp ≤ 10 ¹¹ Ω
Decay time	IEC 61340-2-1	0.5-0.9 seconds Peak voltage U ≤ 150V	< 2 seconds To 10% of initial value (max peak voltage 1000V)



FF48 ESD Fabric		
Black	0048411	
Navy Blue	0048408	

We believe all the information in these pages including technical data to be reliable. However, we make no warranties expressed or implied and assume no liability regarding any use of this information K&K preserves its right to alter the composition and materials used in manufacturing the product